

FORMATO/ <i>FORMAT</i>	31,6X60
ESPESOR/ <i>THICKNESS (mm) / ÉPAISSEUR</i>	9
PRODUCTO/ <i>PRODUCT / PRODUIT</i>	31,6X60 COOL OCRE
TIPO/ <i>KIND / TYPE</i>	ESMALTADO/ <i>GLAZED / ÉMAILLÉ</i>
GRUPO/ <i>GROUP / GROUPE</i>	BIII - GL
NORMA APLICABLE EN 14411 ANEXO L <i>APPLICABLE STANDARD ISO 13006 ANNEX L</i> <i>NORMATIVE APPLICABLE STANDARD ISO 13006 ANNEXE L</i>	

ENSAYOS/ <i>TESTS / TEST</i>		RESULTADOS/ <i>RESULTS / RÉSULTATS</i>	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL <i>UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY</i>	DIMENSIONES	CUMPLE CON LA NORMA
		<i>DIMENSIONS</i>	<i>COMPLIES WITH THE STANDARD</i>
		<i>DIMENSIONS</i>	<i>CONFORME</i>
	UNE- EN ISO 10545-3 ABSORCIÓN DE AGUA <i>UNE- EN ISO 10545-3 WATER ABSORPTION</i> <i>UNE- EN ISO 10545-3 ABSORPTION D'EAU</i>	VALOR MEDIO (%) <i>AVERAGE VALUE (%)</i> <i>VALEUR MOYENNE (%)</i>	16%
		FUERZA DE ROTURA <i>BREAKING STRENGH (N)</i>	600-900 N
		<i>CHARGE MÉCANIQUE (N)</i>	
	UNE- EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN <i>UNE- EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN</i> <i>UNE- EN ISO 10545-4 MODULUS OF RUPTURE</i> <i>UNE- EN ISO 10545-4 RÉSISTANCE À LA FLEXION</i>	RESISTENCIA A LA FLEXIÓN <i>MODULUS OF RUPTURE (N/mm2)</i> <i>RÉSISTANCE À LA FLEXION</i>	15-25 N/mm ²
	UNE- EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO <i>UNE- EN ISO 10545-9 THERMAL RESISTANCE</i> <i>UNE- EN ISO 10545-9 RÉSISTANCE AU CHOC THERMIQUE</i>	RESULTADO <i>RESULT</i> <i>RÉSULTAT</i>	RESISTE <i>RESISTS</i> <i>CONFORME</i>
	UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO <i>UNE-EN-ISO 10545-11 CRAZING RESISTANCE</i> <i>UNE-EN-ISO 10545-11 RÉSISTANCE AU TRESSAILLAGE</i>	RESULTADO <i>RESULT</i> <i>RÉSULTAT</i>	RESISTE <i>RESISTS</i> <i>CONFORME</i>
	UNE- EN ISO 10545-13 RESISTENCIA QUÍMICA <i>UNE- EN ISO 10545-13 CHEMICAL RESISTANCE</i>	CLORURO AMÓNICO <i>AMMONIUM CHLORIDE 100 g/l</i> <i>CHLORURE AMMONIÉ</i>	A
		HIPOCLORITO SÓDICO <i>SODIUM HYPOCHLORITE 20 mg/l</i> <i>HYPOCHLORITE SODIUM</i>	A
		ÁCIDO CLORHÍDRICO <i>HYDROCHLORIC ACID 3%</i> <i>ACIDE CHLORIQUE</i>	CUMPLE CON LA NORMA
	UNE- EN ISO 10545-13 <i>RÉSISTANCE CHIMIQUE</i>	ÁCIDO CÍTRICO <i>CITRIC ACID 100 g/l</i> <i>ACIDE CITRIQUE</i>	<i>COMPLIES WITH THE STANDARD</i>
		HIDRÓXIDO POTÁSICO <i>POTASSIUM HYDROXYDE 30 g/l</i> <i>HYDROXIDE POTASSIQUE</i>	<i>CONFORME</i>
	UNE- EN ISO 10545-14 RESISTENCIA A LAS MANCHAS <i>UNE- EN ISO 10545-14 STAIN RESISTANCE</i> <i>UNE- EN ISO 10545-14 RÉSISTANCE AUX TÂCHES</i>	ÓXIDO VERDE EN ACEITE LIGERO <i>GREEN AGENT IN LIGHT OIL</i> <i>OXYDE VERT À L'HUILE LÉGER</i>	5
		SOLUCIÓN ALCOHÓLICA DE YODO <i>IODINE SOLUTION IN ALCOHOL</i> <i>SOLUTION ALCOOLIQUE D'IODE</i>	5
		ACEITE DE OLIVA <i>OLIVE OIL</i> <i>L'HUILE D'OLIVE</i>	5

OBSERVACIONES:

VºBº LABORATORIO:

